

A nonwoven geotextile fabric supplied by Thrace-LINQ, Inc., is manufactured from Polypropylene staple fiber. The fibers are randomly oriented and form a cohesive / stabilized needle punched fabric for use in many applications, such as separation, drainage, filtration, etc. This fabric has been UV stabilized and is resistant to commonly encountered chemicals, mildew and insects found in soil. .

<i>PROPERTY</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		MARV		MARV	
Grab Tensile Strength	ASTM D-4632	467	N	105	lbs
Grab Elongation	ASTM D-4632	50	%	50	%
Trapezoid Tear	ASTM D-4533	200	N	45	lbs
Puncture (CBR)	ASTM D-6241	1335	N	300	lbs
Permittivity	ASTM D-4491	2.0	sec <sup>-1</sup>	2.0	sec <sup>-1</sup>
A.O.S.	ASTM D-4751	0.212	mm	70	U.S. Sieve
UV Stability (500 hrs)	ASTM D-4355	70	%	70	%
Water Flow Rate	ASTM D-4491	5908	lpm/m <sup>2</sup>	145	gpm/ft <sup>2</sup>

Notes: - Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.  
 - Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

<i>PACKAGING</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		Typical		Typical	
Weight	ASTM D-5261	136	g/m <sup>2</sup>	4.0	oz/yd <sup>2</sup>
Thickness	ASTM D-5199	1.397	mm	55	mils
Roll sizes		3.81 x 109.7	m	12.5 x 360	ft
		4.57 x 109.7	m	15 x 360	ft
Roll Area		418	m <sup>2</sup>	500	yd <sup>2</sup>
		501	m <sup>2</sup>	600	yd <sup>2</sup>

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.